CLAIMS

What is claimed is:

SUB B1

1. An integrated circuit comprising
NMOS transistors in P-wells,
PMOS transistors in N-wells, and
at least one PNP bipolar transistor having
an emitter diffusion which has a doping profile which combines said P-wells with P+ source diffusions of said PMOS transistors, and
a base diffusion which at least partly underlies said emitter diffusion, and which has a doping profile which is at least partly the said as said N-wells;
said emitter and base diffusions jointly defining an emitter:base ratio of near-junction dopants, measured at 75% and 125% of the emitter-base junction depth, which is greater than two to one.

2. The integrated circuit of Claim 1, 4, 7, wherein said emitter diffusion further comprises a P+ diffusion which is also implanted into the sources of said PMOS transistors.

SUB B2

3. The integrated circuit of Claim 1, 4, 7, further comprising a blanket P-type diffusion component having a peak concentration depth more than twice that of said p-well.

4. An integrated circuit comprising

NMOS and PMOS transistors, and

a PNP bipolar transistor which includes

a P-type emitter diffusion, having at least one implanted diffusion profile which is the same as at least one implanted diffusion component of p-wells which contain at least some of said NMOS transistors;

an N-type base diffusion, having at least one implanted diffusion profile which is the same as at least one diffusion component of n-wells which contain at least some of said PMOS transistors;

wherein the peak of said p well is no deeper than the peak of said n well.

B

5. The integrated circuit of Claim 1, 4, 7, wherein said emitter diffusion further comprises a P+ diffusion which is also implanted into the sources of said PMOS transistors.

6. The integrated circuit of Claim 1, 4, 7, further comprising a blanket P-type diffusion component having a peak concentration depth more than twice that of said p-well.

7. An integrated circuit comprising

NMOS transistors in P-wells;

PMOS transistors in N-wells;

a blanket p-type diffusion, having a peak concentration depth more than twice that of said P-wells; and

at least one PNP bipolar transistor having

an emitter diffusion which has a doping profile which combines said P-wells with P+ source diffusions of said PMOS transistors,

a base diffusion which at least partly underlies said emitter diffusion, and which has a doping profile which is at least partly the said as said N-wells, and

a collector diffusion which at least partly underlies said base diffusion, and which has a doping profile which is at least partly the same as said blanket p-type diffusion;

said emitter and base diffusions jointly defining an emitter:base ratio of near-junction dopants, measured at 75% and 125% of the emitter-base junction depth which is greater than two to one.

B

8. The integrated circuit of Claim 1, 4, 7, wherein said emitter diffusion further comprises a P+ diffusion which is also implanted into the sources of said PMOS transistors.

9. An integrated circuit fabrication method, comprising the steps of:

(a) implanting p-type dopants into p-well locations and PNP emitter locations, but not into all locations;

(b) implanting n-type dopants into n-well locations and PNP emitter locations, but not into all locations;

(c) implanting p-type dopants into PMOS source/drain locations and PNP emitter locations, with a stopping distance less than half of that used in said step (a); and

(d) implanting p-type dopants overall, with a stopping distance more than twice that used in said step (c);

whereby emitter efficiency of resulting PNP transistors is improved.